

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 November 2001 (22.11.2001)

PCT

(10) International Publication Number
WO 01/88247 A1

(51) International Patent Classification⁷: **D04H 1/46**

(21) International Application Number: **PCT/US01/15808**

(22) International Filing Date: **16 May 2001 (16.05.2001)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:
60/204,721 **16 May 2000 (16.05.2000)** **US**

(71) Applicant: **POLYMER GROUP INC.** [US/US]; 4838
Jenkins Avenue, North Charleston, SC 29406 (US).

(72) Inventors: **CARLSON, Cheryl**; 100 Raspberry Court,
Willow Springs, NC 27592 (US). **ELVES, John**; P.O. Box
15, NL-5430 AA Cuijk (NL).

(74) Agent: **GEIMER, Stephen, D.**; Rockey, Milnamow &
Katz, Ltd., Suite 4700, Two Prudential Plaza, 180 North
Stetson, Chicago, IL 60601 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF MAKING NONWOVEN FABRIC COMPRISING SPLITTABLE FIBERS



(57) Abstract: The present invention relates generally to a method of making nonwoven fabrics, wherein the fabrics are formed from splittable filaments or staple length fibers having a plurality of sub-components which are at least partially separable. The filaments or fibers are at least partially separated into their sub-components attendant to hydroentanglement, which can be effected on a three-dimensional image transfer device (25). Improved physical properties, including improved tensile strength, elongation, and Taber Abrasion resistance are achieved.

**METHOD OF MAKING NONWOVEN
FABRIC COMPRISING SPLITTABLE FIBERS**

Technical Field

5 The present invention relates generally to a method of making a nonwoven fabric exhibiting enhanced physical properties, including improved drape and hand, and more particularly to a method of making a nonwoven fabric comprising hydroentangling a precursor web at least partially comprising splittable filaments or staple length fibers, whereby the precursor web is imaged and patterned on a three-dimensional image transfer device.

10 **Background Of The Invention**

Nonwoven fabrics are used in a wide variety of applications where the engineered qualities of the fabric can be advantageously employed. These types of fabrics differ from traditional woven or knitted fabrics in that the fabrics are produced directly from a fibrous mat eliminating the traditional textile manufacturing processes of multi-step yarn preparation, and weaving or knitting. Entanglement of the fibers or filaments of the fabric acts to provide the fabric with a substantial level of integrity.

U.S. Patent No. 3,485,706, to Evans, hereby incorporated by reference, discloses processes for effecting the hydroentanglement of nonwoven fabrics. More recently, hydroentanglement techniques have been developed which impart images or patterns to the entangled fabric by effecting hydroentanglement on three-dimensional image transfer devices. Such three-dimensional image transfer devices are disclosed in U.S. Patent No. 5,098,764, and U.S. Patent No. 5,244,711, hereby incorporated by reference, with the use of such image transfer devices being desirable for providing fabrics with the desired physical properties as well as an aesthetically pleasing appearance.

For specific applications, a nonwoven fabric must exhibit a combination of specific physical characteristics. For example, for some applications it is desirable that nonwoven fabrics exhibit both wet and dry strength characteristics comparable to those of traditional woven or knitted fabrics. While nonwoven

fabrics exhibiting sufficient strength can typically be manufactured by selection of appropriate fiber or filament composition, fabric basis weight, and specific process parameters, the resultant fabrics may not exhibit the desired degree of drapeability and hand as traditional woven or knitted fabrics exhibiting comparable strength. While it is known in the prior art to treat nonwoven fabrics with binder compositions for enhancing their strength and durability, such treatment can undesirably detract from the drape and hand of the fabric.

While manufacture of nonwoven fabrics from homopolymer, single component filaments or fibers is well-known, use of multi-component "splittable" fibers or filaments can be advantageous for some applications. These types of splittable fibers or filaments comprise plural sub-components, typically comprising two or more different polymeric materials, with the sub-components arranged in side-by-side relationship along the length of the filaments or fibers. Various specific cross-sectional configurations are known, such as segmented-pie sub-components, islands-in-the-sea sub-components, flower-like sub-components, side-by-side sub-component arrays, as well as a variety of additional specific configurations.

The sub-components of splittable fibers or filaments can be separated by various chemical or mechanical processing techniques. For example, portions of the multi-component fiber or filament can be separated by heating, needlepunching, or water jet treatment. Suitable chemical treatment of some types of multi-component fibers or filaments acts to dissolve portions thereof, thus at least partially separating the sub-components of the fibers or filaments.

U.S. Patent No. 4,476,186, to Kato et al., hereby incorporated by reference, discloses various forms of multi-component fibers and filaments, and contemplates formation of structures wherein splitting of the fibers or filaments on one or more surfaces of these structures provides desired physical properties. This patent particularly contemplates treatment of the fibrous structures with polyurethane compositions, to thereby form synthetic leather-like materials.

The present invention contemplates formation of nonwoven fabrics exhibiting desired physical properties, including wet and dry strength characteristics, as well as good drapeability and hand.

Summary Of The Invention

5 The present invention is directed to a method of making a nonwoven fabric which includes imaging and patterning of a precursor web by hydroentanglement on a three-dimensional image transfer device. Notably, the precursor web at least partially comprises splittable filaments or staple length
10 fibers, each of which comprises plural sub-components which are at least partially separable from each other. Attendant to hydroentanglement, the high pressure liquid streams impinging upon the precursor web act to at least partially separate the sub-components of the splittable filaments or fibers from each other, thus creating filament or fiber components having relatively small deniers. Because of the relatively reduced bending modules exhibited by the fine-denier
15 sub-components, imaging and entanglement of the web is enhanced for fabric formation. The resultant fabric exhibits relatively high wet and dry tensile strengths, without resort to application of binder compositions or the like, and thus exhibits desirable drapeability and hand. By virtue of the fabric's integrity, post-formation processes, such as jet dyeing, can be effected without the
20 application of a binder composition, as is typically required.

 In accordance with the disclosed embodiment, the present method comprises providing a precursor web at least partially comprising splittable, staple length fibers, wherein each of the splittable fibers comprises plural sub-components at least partially separable from each other. In presently preferred
25 embodiments, splittable fibers having so-called segmented-pie and swirled configurations have been employed.

 The present method further comprises providing a three-dimensional image transfer device having a foraminous forming surface. This type of image transfer device includes a distinct surface pattern or image which is imparted to
30 the precursor web during fabric formation by hydroentanglement.

The precursor web is positioned on the image transfer device, with hydroentanglement effected by application of a plurality of high-pressure liquid streams. The high-pressure liquid streams act to entangle and integrate the fibers of the precursor web. By virtue of their high energy, the liquid streams at least partially separate the sub-components of the splittable fibers, thus enhancing the clarity of the image imparted to the precursor web from the image transfer device.

Depending upon the specific application for the resultant nonwoven fabric, various types of splittable, staple length fibers can be employed. In current embodiments, splittable staple length fibers have been used comprising nylon, and one of 1,4 cyclohexamethyl terephthalate and polyethylene terephthalate sub-components. It is also contemplated that the splittable fibers may be blended with staple length fibers selected from the group consisting of nylon, polyester and rayon.

Cross-lapping of a carded precursor web prior to positioning on the image transfer device desirably enhances the effect of the hydroentanglement treatment in patterning and imaging the precursor web. By virtue of the high degree of integrity imparted to the web attendant to hydroentanglement, the present method further contemplates that the nonwoven fabric can be jet dyed, subsequent to hydroentanglement, preferably without the application of a binder composition thereto.

A nonwoven fabric embodying the principles of the present invention can be formed to exhibit low air permeability, with the fabric thus being suitable for applications where the barrier properties of a fabric are important, such as for medical gowns and the like. The fabric is formed from a fibrous matrix at least partially comprising splittable, spunbond filaments, wherein each of the splittable filaments comprises plural sub-components at least partially separated from each other. Notably, the fabric has been found to exhibit desirably high strength and elongation, exhibiting permeability lower than a comparable melt blown fabric, while being three to four times stronger, with three to five times

more elongation. Aside from medical applications, potential uses include filter media and personal hygiene articles.

Other features and advantages of the present invention will become readily apparent from the following detailed description, the accompanying
5 drawings, and the appended claims.

Brief Description Of The Drawings

FIGURE 1 is a diagrammatic view of a hydroentangling apparatus for practicing the method of the present invention;

FIGURES 2-4 are views illustrating the configuration of a "left-hand
10 twill" three-dimensional image transfer device;

FIGURES 5A and 5B are isometric and plan views, respectively, of the configuration of a "pique" three-dimensional image transfer device;

FIGURES 6 is a diagrammatic plan view of the configuration of a "wave" pattern of a three-dimensional image transfer device;

FIGURE 7 is a diagrammatic plan view of the configuration of the
15 "enlarged basketweave" pattern of a three-dimensional image transfer device;

FIGURE 7A is a diagrammatic plan view of the configuration of the "placemat" pattern of a three-dimensional image transfer device;

FIGURES 8A to 8F are photomicrographs of nonwoven fabrics including
20 fabrics formed in accordance with the present invention; and

FIGURE 9 shows illustrations of a three-dimensional image transfer device having a "octagon and squares" pattern.

Detailed Description

While the present invention is susceptible of embodiment in various
25 forms, there is shown in the drawings, and will hereinafter be described, preferred embodiments of the invention, with the understanding that the present disclosure is to be considered as an exemplification of the invention, and is not intended to limit the invention to the specific embodiment illustrated.

The present invention is directed to a method of forming nonwoven
30 fabrics by hydroentanglement, wherein imaging and patterning of the fabrics is

enhanced by hydroentanglement on a three-dimensional image transfer device. Enhanced physical properties of the resultant fabric, including enhanced patterning and imaging, is achieved by providing a precursor web at least partially comprising splittable filaments or fibers, that is, filaments or fibers which can each be divided into plural sub-components. Through the use of high-pressure water jets for effecting hydroentangling and imaging, these splittable fibers or filaments are at least partially separated into their sub-components, with the high pressure water jets acting on these sub-components. By virtue of the reduced bending modules of these relatively fine-denier sub-components, enhanced imaging and patterning of the fabric is achieved. Notably, the drapeability and hand of the resultant fabric is enhanced, thus enhancing versatile use of the fabric.

With reference to FIGURE 1, therein is illustrated an apparatus for practicing the present method for forming a nonwoven fabric. The fabric is formed from a precursor web comprising a fibrous matrix which typically comprises staple length fibers, but which may comprise substantially continuous filaments. The fibrous matrix is preferably carded and cross-lapped to form the precursor web, designated P. In accordance with the present invention, the precursor web at least partially comprises splittable staple length fibers or filaments.

FIGURE 1 illustrates a hydroentangling apparatus for forming nonwoven fabrics in accordance with the present invention. The apparatus includes a foraminous forming surface in the form of a belt 10 upon which the precursor web P is positioned for pre-entangling by entangling manifold 12. Pre-entangling of the precursor web, prior to imaging and patterning, is subsequently effected by movement of web P sequentially over a drum 14 having a foraminous forming surface, with entangling manifold 16 effecting entanglement of the web. Further entanglement of the web can be effected on the foraminous forming surface of a drum 18 by entanglement manifold 20, with subsequent

movement of the web over successive foraminous drums 22 for successive entangling treatment by entangling manifolds 24, 24'.

The entangling apparatus of FIGURE 1 further includes an imaging and patterning drum 25 comprising a three-dimensional image transfer device for effecting imaging and patterning of the now-entangled precursor web. The image transfer device includes a movable imaging surface which moves relative to a plurality of entangling manifolds 26 which act in cooperation with three-dimensional elements defined by the imaging surface of the image transfer device to effect imaging and patterning of the fabric being formed.

FIGURE 1 also illustrates a J-box or scray 23 which can be employed for supporting the precursor web P as it is advanced onto the image transfer device, to thereby minimize tension within the precursor web. By controlling the rate of the advancement of the precursor web onto the imaging surface to minimize, or substantially eliminate, tension within the web, enhanced hydroentanglement of the precursor web can be effected. Hydroentanglement results in portions of the precursor web being displaced from on top of the three-dimensional surface elements of the imaging surface to form an imaged and patterned nonwoven fabric. By use of relatively high-pressure hydroentangling jets, the splittable fibers or filaments of the precursor web are at least partially separated into sub-components, with enhanced imaging and patterning thus resulting.

The enhanced imaging and patterning achieved through practice of the present invention is evidenced by the appended microphotographs of FIGURES 8A to 8F. The fabric samples designated "CLC-205" were formed from conventional, non-splittable fibers, comprising a 50%/50% blend of polyethylene terephthalate (PET)/nylon fibers. The samples designated "CLC-069B" comprise 100% splittable staple length fibers, having 16 sub-components in a segmented-pie configuration. This type of fiber, available from Fiber Innovation Technology, Inc., under the designation Type 502, comprises a PET/nylon blend, with 8 sub-component segments each of PET and nylon. This type of fiber has a nominal denier of 3.0, with each sub-component having a

denier of 0.19. Samples designated "CLC-096" were formed from Unitika splittable staple length fibers, production designation N91, having a denier of 2.5, with 20 sub-components in a segmented-pie configuration, with each sub-component having a 0.12 denier. These splittable fibers also comprise a blend of PET/nylon.

With reference to the microphotographs, it will be observed from the "top light" and "dark field" views that by comparison of the control sample (CLC-205) with sample CLC-069B (F.I.T. splittable fibers), that the splittable fiber sample shows more uniform coverage, with a clearer image, or better image clarity. The dark field comparison shows a much deeper image than that achieved with the control non-splittable fiber sample, with bundling or roping of the entwined sub-denier fiber components being evident. It is believed that the improved image clarity (i.e., less fuzzy pattern) is achieved by virtue of the enhanced fiber entanglement, which is achieved by the relatively reduced bending modules of the sub-components of the splittable fibers.

Comparison of the Unitika splittable fiber sample (CLC-096A) with the control, non-splittable fiber sample also shows improved image clarity, with better definition of the imaged pattern. Interconnecting regions of the pattern, at which less fiber is present, are not as well defined in the control, non-splittable fiber sample, as in the sample formed from splittable fibers in accordance with the present invention. Comparison of the two splittable fiber samples, CLC-069B and CLC-096A, shows the former to provide better defined fiber transition regions, which is believed to be achieved by virtue of this type of fiber being more easily splittable attendant to hydroentangling processing. Very fine sub-denier composite fibers can be hard to make, and can complicate splitting of the fibers, such as by hydroentangling processes. This phenomenon suggests optimum results may be achieved through use of splittable fibers having a certain maximum number of splittable sub-components.

Examples

Appended Table 1 (2 pages) sets forth test data regarding various sample nonwoven fabrics formed in accordance with the principles of the present invention, including comparison to control samples. Reference to various image transfer devices (ITD) refers to configurations illustrated in the appended drawings. Reference to "100 x 98" and "22 x 23" refers to foraminous forming screens. Reference to "20 x 20", "12 x 12", "14 x 14", and "6 x 8" refers to a three-dimensional image transfer device having an array of "pyramidal" three-dimensional surface elements, configured generally in accordance with FIGURE 9 of U.S. Patent No. 5,098,764, hereby incorporated by reference. The referenced "placemat" image transfer device is a composite image comprised of a background "tricot" pattern (in accordance with U.S. Patent No. 5,670,234, hereby incorporated by reference), a central "vine and leaf" pattern, and a circumferential "lace" pattern. The overall dimension of the rectangular image is approximately 10 inches by 13 inches. The approximate depth of the image in the background region is 0.025 inches, and in the "vine and leaf" and "lace" regions is 0.063 inches. Reference to "prebond" refers to a fabric tested after pre-entangling, but formed without imaging on a image transfer device.

For manufacture of the fabric samples, an apparatus as illustrated in FIGURE 1 was employed. Pre-entangling manifolds at drums 14, 18, and 22 were operated at 40 bar, 50 bar, 80 bar, and 81 bar, respectively, unless otherwise noted. The three manifolds 26 at the image transfer device 25 were operated at or in excess of 2500 psi, unless otherwise noted.

A further aspect of the present invention contemplates a nonwoven fabric formed from spunbond filaments, wherein each of the filaments comprises plural sub-components which are at least partially separated from each other. Table 2 sets forth certain physical properties of spunbond, as well as staple length, fabrics formed in accordance with the present invention on a foraminous forming surface in the form of a 100 mesh forming screen. As will be observed, fabrics formed in accordance with the present invention from splittable, spunbond filaments, all exhibited very good Taber Abrasion resistance to roping,

greater than 35 cycles. In the sample in which the filaments were formed from polyester and polyethylene (8-segment crescent configuration), the fabric exhibited a ratio of machine direction tensile strength to basis weight of 19. For other samples formed from spunbond filaments, comprising polyester and nylon,
5 the ratio of machine direction tensile strength to basis weight was at least about 23. As will be noted, all fabrics formed from spunbond filaments exhibit air permeability no greater than about 26 cfm (ft.³/min.), which can be desirable for certain applications.

Table 2 also shows fabrics formed in accordance with the present
10 invention from splittable fibers. These samples were formed from bicomponent staple fibers comprising polyester and nylon, and exhibited a ratio of machine direction tensile strength to basis weight of at least about 22; these samples all exhibit a Taber Abrasion resistance to roping greater than 35 cycles (i.e., no roping).

15 Table 2 sets forth comparative data for a representative polyester and pulp fabric (designated PET/pulp). The greater tensile strength, elongation, and Taber Abrasion of fabrics formed in accordance with the present invention will be noted.

20 From the foregoing, numerous modifications and variations can be effected without departing from the true spirit and scope of the novel concept of the present invention. It is to be understood that no limitation with respect to the specific embodiment disclosed herein is intended or should be inferred. The disclosure is intended to cover, by the appended claims, all such modifications as fall within the scope of the claims.

Table 1

Physical Property	CLC-220-NF	CLC-098A-NF	Delta	CLC-098B-NF	Delta	CLC-098C-NF	Delta
Image	100x98 Screen	Wave	220 v. 098A	Oct/Sq.	220 v. 098B	22x23	220 v. 098C
Weight	2.06	2.15	4%	2.08	1%	2.07	0%
Bulk	0.014	0.021	33%	0.019	26%	0.019	26%
Tensile - Dry [MD]	37.5	42.7	12%	41.8	10%	42.4	12%
Tensile - Wet [MD]	35.2	39.8	12%	34.1	-3%	45.9	23%
	-6%	-7%		-18%		8%	
Elongation - Dry [MD]	35.4	53.9	34%	40.0	11%	34.3	-3%
Elongation - Wet [MD]	44.4	44.7	1%	41.0	-8%	42.3	-5%
	20%	-17%		2%		19%	
Tensile - Dry [CD]	23.1	20.6	-11%	16.9	-27%	23.7	3%
Tensile - Wet [CD]	16.0	18.2	12%	18.4	13%	18.4	13%
	-31%	-12%		8%		-23%	
Elongation - Dry [CD]	128.6	98.8	-23%	96.8	-25%	93.0	-28%
Elongation - Wet [CD]	122.8	109.3	-11%	103.0	-16%	87.6	-29%
	-5%	10%		6%		-6%	
Handle [MD]	37	21	-43%				
Handle [CD]	4	3	-25%				
Cantilever Bend [MD]	7.7	7.2	-6%				
Cantilever Bend [CD]	3.1	2.7	-13%				
Absorbency Capacity	676	805	16%	698	3%	716	6%
Air Perm	85	111	23%	386	78%	407	79%
Modulus 3% [MD]	1.03	0.68	-34%		#DIV/0!		#DIV/0!
Modulus 5% [MD]	1.17	0.78	-33%		#DIV/0!		#DIV/0!
Modulus 10% [MD]	1.14	0.83	-27%		#DIV/0!		#DIV/0!
Modulus 20% [MD]	1.03	0.9	-13%		#DIV/0!		#DIV/0!
Modulus 3% [CD]	0.05	0.015	-70%		#DIV/0!		#DIV/0!
Modulus 5% [CD]	0.05	0.015	-70%		#DIV/0!		#DIV/0!
Modulus 10% [CD]	0.05	0.02	-60%		#DIV/0!		#DIV/0!
Modulus 20% [CD]	0.05	0.025	-50%		#DIV/0!		#DIV/0!
Load @ 10% Elong. [MD]	12.29	8.2	-33%		#DIV/0!		#DIV/0!
Load @ 10% Elong. [CD]	0.41	0.13	-68%		#DIV/0!		#DIV/0!
Load @ 20% Elong. [MD]	23.01	18.3	-20%		#DIV/0!		#DIV/0!
Load @ 20% Elong. [CD]	0.94	0.34	-64%		#DIV/0!		#DIV/0!

Table 1

Physical Property	CLC-220-NF	CLC-098A-NF	Delta	CLC-205-NF	CLC-069B-NF	Delta
Image	100x98 Mesh	Wave	220 v. 098A	Wave	Wave	205 v. 069B
Weight	2.06	2.15	4%	3.1	3	-3%
Bulk	0.014	0.021	33%	0.039	0.026	-33%
Tensile - Dry [MD]	37.5	42.7	12%	68.3	59.1	-13%
Tensile - Wet [MD]	35.2	39.8	12%	66.9	59.4	-11%
Delta [Dry v. Wet]	-6%	-7%		-2%	1%	
Elongation - Dry [MD]	35.4	53.9	34%	64.6	44.3	-31%
Elongation - Wet [MD]	44.4	44.7	1%	65.5	49.1	-25%
Delta [Dry v. Wet]	20%	-17%		1%	10%	
Tensile - Dry [CD]	23.1	20.6	-11%	36.5	28.2	-23%
Tensile - Wet [CD]	16.0	18.2	12%	36.2	27.5	-24%
Delta [Dry v. Wet]	-31%	-12%		-1%	-2%	
Elongation - Dry [CD]	128.6	98.8	-23%	172.2	117.8	-32%
Elongation - Wet [CD]	122.8	109.3	-11%	149.0	118.4	-21%
Delta [Dry v. Wet]	-5%	10%		-13%	1%	
Handle [MD]	37	21	-43%	35	46	23%
Handle [CD]	4	3	-25%	8	7	-13%
Canilever Bend [MD]	7.7	7.2	-6%			#DIV/0!
Canilever Bend [CD]	3.1	2.7	-13%			#DIV/0!
Absorbency	676	805	16%			#DIV/0!
Air Perm	85	111	23%			#DIV/0!
Modulus 3% [MD]	1.03	0.68	-34%	0.27	0.45	40%
Modulus 5% [MD]	1.17	0.78	-33%	0.39	0.68	43%
Modulus 10% [MD]	1.14	0.83	-27%	0.54	0.9	40%
Modulus 20% [MD]	1.03	0.9	-13%	0.72	1.07	33%
Modulus 3% [CD]	0.05	0.015	-70%	0.02	0.01	-50%
Modulus 5% [CD]	0.05	0.015	-70%	0.02	0.01	-50%
Modulus 10% [CD]	0.05	0.02	-60%	0.02	0.01	-50%
Modulus 20% [CD]	0.05	0.025	-50%	0.03	0.02	-33%
Load @ 10% Elong. [MD]	12.29	8.2	-33%	5.86	10.11	42%
Load @ 10% Elong. [CD]	0.41	0.13	-68%	0.12	0.4	70%
Load @ 20% Elong. [MD]	23.01	18.3	-20%	15.22	22.85	33%
Load @ 20% Elong. [CD]	0.94	0.34	-64%	0.3	0.97	69%

Table 2

Sample ID	Shape	Polymer Combination	Fiber Process	Foraminous Surface
2.3 EFP		PET/Pulp	staple	
91-51-04	8-seg crescent	PET/PE	bicomponent spunbond	100 Mesh
91-51-08	8-seg crescent	PET/Nylon	bicomponent spunbond	100 Mesh
23-12-02	16-seg pie	PET/Nylon	bicomponent spunbond	100 Mesh
23-12-03	16-seg pie	PET/Nylon	bicomponent spunbond	100 Mesh
23-12-04	16-seg pie	PET/Nylon	bicomponent spunbond	100 Mesh
CLC-2100	seg pie	PET/Nylon	bicomponent staple	100 Mesh
CLC-3000	seg pie	PET/Nylon	bicomponent staple	100 Mesh
CLC-4000	seg pie	PET/Nylon	bicomponent staple	100 Mesh

Sample ID	Basis Weight		Air	MD Grab Tensile		MDT/BW	MDT/BW % of EFP	MD Grab Elongation %
	gsm	oz/yd ²	cfm	g/cm	lb/in			
2.3 EFP	77.487	2.3	36		38	17		
91-51-04	96	2.85	11	9659	54	19	112%	44
91-51-08	113	3.35	14	14469	81	24	142%	50
23-12-02	76.83	2.28	22	11750	66	29	170%	44
23-12-03	76.20	2.26	18	10757	60	27	157%	41
23-12-04	78.32	2.32	26	9624	54	23	136%	37
CLC-2100	76.10	2.26	34	9664	54	24	141%	45
CLC-3000	78.34	2.33	29	10429	58	25	148%	43
CLC-4000	81.52	2.42	27	9576	54	22	130%	38

Sample ID	CD Grab		CDT/BW	CDT/BW % of EFP	CD Grab Elongation %	Energy	Taber Abrasion		HH cm
	g/cm	lb/in				hp-lr/lb	til roping	til fail	
2.3 EFP		21	9				35	182	24
91-51-04	3247	18	6	71%	115	2.12	no	181	
91-51-08	6184	35	10	115%	100	1.8	no roping	>250	32.9
23-12-02	5532	31	14	151%	99	1.14	no roping	>250	33.5
23-12-03	3729	21	9	103%	82	1.86	no roping	>250	
23-12-04	4470	25	11	120%	88	2.72	no roping	>250	
CLC-2100	4553	25	11	125%	109	1.27	no roping	189	
CLC-3000	4388	25	11	117%	102	1.81	no roping	>250	
CLC-4000	4147	23	10	107%	110	2.45	no roping	>250	23.3

WHAT IS CLAIMED IS:

1. A method of making a nonwoven fabric, comprising the steps of:
providing a precursor web at least partially comprising splittable, staple
length fibers, wherein each of said splittable fibers comprises plural sub-
5 components at least partially separable from each other;
providing a three-dimensional image transfer device having a foraminous
forming surface;

positioning said precursor web on said image transfer device, and
hydroentangling said precursor web with a plurality of liquid streams to thereby
10 at least partially separate the sub-components of said splittable fibers and impart
an image from said image transfer device to said precursor web to form a
nonwoven fabric.

2. A method of making a nonwoven fabric in accordance with claim
1, wherein

15 said step of providing set precursor web includes providing splittable,
staple length fibers comprising nylon sub-components and one of 1,4
cyclohexamethyl terephthalate and polyethylene terephthalate.

3. A method of making a nonwoven fabric in accordance with claim
1, including:

20 jet dyeing said nonwoven fabric.

4. A method of making a nonwoven fabric in accordance with claim
1, wherein:

25 said step of providing said precursor web includes providing said web
with a blend of said splittable staple length fibers, and fibers selected from the
group consisting of nylon, polyester and rayon.

5. A method of making a nonwoven fabric in accordance with claim
1, including:

cross-lapping said precursor web prior to positioning on said image
transfer device.

6. A method of making a nonwoven fabric in accordance with claim 1, wherein:

said step of providing said precursor web includes providing said splittable fibers with a denier of about 2.5 to 3.5, with sub-components of said
5 splittable fibers each having a denier of about 0.1 to 0.3.

7. A nonwoven fabric, comprising:

a fibrous matrix comprising splittable, staple length fibers, wherein each of said splittable fibers comprises plural sub-components at least partially separated from each other, said fabric exhibiting a ratio of machine direction
10 tensile strength to basis weight of at least about 22.

8. A nonwoven fabric in accordance with claim 7, wherein:
said splittable staple length fibers comprise polyester and nylon.

9. A nonwoven fabric in accordance with claim 8, wherein:
said splittable, staple length fibers have a segmented pie configuration.

10. A nonwoven fabric in accordance with claim 7, wherein:
said fabric exhibits a Taber Abrasion resistance to roping greater than 35
cycles.

11. A nonwoven fabric, comprising:

a fibrous matrix comprising splittable, spunbond filaments, wherein each
20 of said splittable filaments comprises plural sub-components at least partially separated from each other, said fabric exhibiting a ratio of machine direction tensile strength to basis weight of at least about 19, and a Taber Abrasion resistance to roping greater than 35 cycles.

12. A nonwoven fabric in accordance with claim 11, wherein:

said splittable filaments comprise polyester and polypropylene.

13. A nonwoven fabric in accordance with claim 11, wherein:

said splittable filaments comprise polyester and nylon, and said ratio is at
least about 23.

14. A nonwoven fabric in accordance with claim 13, wherein:

said splittable filaments have an 8-segment crescent configuration.

15. A nonwoven fabric in accordance with claim 13, wherein:
said splittable filaments have a 16-segment pie configuration.
16. A nonwoven fabric in accordance with claim 11, wherein:
said nonwoven fabric exhibits permeability no greater than about 26 cfm.

5

1/10





FIG. 1


2/10

FIG. 2




-ALL DIMS. (mm).
-ALL DIMS. APPROX.

FIG. 3



-ALL DIMS. (mm)
-ALL DIMS. APPROX.

FIG. 4



3/10

FIG. 5A






FIG. 5B




4/10

FIG. 6



5/10

FIG. 7




ITD Depth: 0.13" Element Depth 0.05"

6/10

FIG. 7A

Photograph of lace fabric formed on lace ITD



7/10

FIG. 8A

Top light

Control sample: CLC-205-NF

Sample: CLC-069B-NF




FIG. 8B

Darkfield light

Control sample: CLC-205-NF

Sample: CLC-069B-NF



8/10

FIG. 8C

Top light

Control sample: CLC-205-NF

Sample: CLC-096A-NF




top2

FIG. 8D

Darkfield light

Control sample: CLC-205-NF

Sample: CLC-096A-NF



dkfield2

9/10

FIG. 8E

Top light

Sample: CLC-069B-NF

Sample: CLC-096A-NF




FIG. 8F

Darkfield light



Sample: CLC-069B-NF

Sample: CLC-096A-NF




10/10


FIG. 9



SECT. A - A



SECT. B - B



SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US01/15808

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : D04H 1/46

US CL : 28/104, 106; 442/361, 408

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 28/104, 105, 106, 103; 442/361, 362, 363, 364, 365, 408; 428/364, 365, 370, 373, 374, 372

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X -- Y	US 4,476,186 A (KATO et al) 09 October 1984, col. 6, lines 6-25.	7-16 <u>1-6</u>
Y	US 5,827,597 A (JAMES et al) 27 October 1998, see entire disclosure.	1-6
A	US 5,888,916 A (TADOKORO et al) 30 March 1999.	1-16
A, P	US 6,228,490 B1 (NAGANO et al) 08 May 2001.	1-16
A, P	US 6,103,061 A (ANDERSON et al) 15 August 2000.	1-16
A, P	US 6,200,669 B1 (MARMON et al) 13 March 2001.	1-16

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"E" earlier document published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"G" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

10 SEPTEMBER 2001

Date of mailing of the international search report

25 OCT 2001

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

AMY VANATTA

Telephone No. (703) 308-0861

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US01/15808

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,965,084 A (NISHIJIMA) 12 October 1999.	

PATENT COOPERATION TREATY

PCT

INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference 15879	FOR FURTHER ACTION		see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.
International application No. PCT/US 02/ 35120	International filing date (day/month/year) 31/10/2002	(Earliest) Priority Date (day/month/year) 20/12/2001	
Applicant KIMBERLY-CLARK WORLDWIDE, INC.			

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 03 sheets.



It is also accompanied by a copy of each prior art document cited in this report.

1. Basis of the report

- a. With regard to the **language**, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.



the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).

- b. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international search was carried out on the basis of the sequence listing :



contained in the international application in written form.



filed together with the international application in computer readable form.



furnished subsequently to this Authority in written form.



furnished subsequently to this Authority in computer readable form.



the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.



the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished

2. ☐ **Certain claims were found unsearchable** (See Box I).

3. ☐ **Unity of invention is lacking** (see Box II).

4. With regard to the **title**,



the text is approved as submitted by the applicant.



the text has been established by this Authority to read as follows:

5. With regard to the **abstract**,



the text is approved as submitted by the applicant.



the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.

6. The figure of the **drawings** to be published with the abstract is Figure No.



as suggested by the applicant.



because the applicant failed to suggest a figure.



because this figure better characterizes the invention.

7



None of the figures.

Information on patent family members

International Application No.

PCT/US 02/35120

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9920821	A	29-04-1999	US 6103061 A	15-08-2000
			AU 746558 B2	02-05-2002
			AU 1098299 A	10-05-1999
			CA 2305552 A1	29-04-1999
			EP 1023476 A1	02-08-2000
			JP 2001520332 T	30-10-2001
			TW 396226 B	01-07-2000
			WO 9920821 A1	29-04-1999
WO 0188247	A	22-11-2001	AU 6166001 A	26-11-2001
			EP 1282737 A1	12-02-2003
			WO 0188247 A1	22-11-2001
			US 2002028623 A1	07-03-2002
WO 9823804	A	04-06-1998	US 6200669 B1	13-03-2001
			AU 729553 B2	01-02-2001
			AU 5454198 A	22-06-1998
			BR 9713419 A	24-10-2000
			CN 1245542 A	23-02-2000
			EP 0941379 A1	15-09-1999
			WO 9823804 A1	04-06-1998
			US 2001037850 A1	08-11-2001